

## B7303

|   |                       |                        |
|---|-----------------------|------------------------|
| Fabric / Weefsel / Tissu / Gewebe / Tejido  | 100 % PES / 1100 dtex |                        |
| Total weight / Gewicht totaal / Poids total / Totalgewicht / Peso total   | 550 g/m <sup>2</sup>  | DIN EN ISO 2286/2 1998 |
| Characteristics / Eigenschappen / Caractéristiques / Eigenschaften / Characteristics  | Foodgrade             |                        |
| Lacquering / Vernis / Lackierung / Lacado   | -/-                   |                        |
| Embossing / Kalander / Calandre / Lackierung / Embossing  | Dull                  |                        |
| Breaking strength Warp<br>Treksterkte Ketting<br>Résistance rupture Chaîne<br>Höchstzugkraft Kette<br>Resistencia a la ruptura Urdimbre   | 2500 N/5cm            | EN ISO 1421/1 1998     |
| Breaking strength Weft<br>Treksterkte Inslag<br>Résistance rupture Trame<br>Höchstzugkraft Schuss<br>Resistencia a la ruptura Trama   | 1800 N/5cm            | EN ISO 1421/1 1998     |
| Tear strength Warp<br>Scheurweerstand Ketting<br>Résistance à la déchirure Chaîne<br>Weiterreisskraft Kette<br>Resistencia a la rasgadura Urdimbre  | 250 N                 | DIN 53363 2003         |
| Tear strength Weft<br>Scheurweerstand Inslag<br>Résistance à la déchirure Trame<br>Weiterreisskraft Schuss<br>Resistencia a la rasgadura Trama  | 250 N                 | DIN 53363 2003         |
| Adhesion / Hechting / Adhérence / Haftung / Adherencia  | 90 N/5cm              | EN ISO 2411 2000       |
| Temperature resistance<br>Temperatuursbestendigheid<br>Tenue à la température<br>Temperatursbeständigkeit<br>Resistencia à la temperatura   | -30/+70 °C            | DIN EN 1876/2 1998     |
| Light fastness (Except white and (half-)transparent)<br>Lichtechtheid (Uitgezonderd wit en (half-)transparent)<br>Tenue à la lumière (Excepté en blanc et (semi-)transparent)<br>Lichtechtheit (Ausnahme weiss und (semi-)transparent)<br>Resistencia a la luz (Excepto blanco / (semi-)transparente) | 7-8                   | ISO 105 B02 1988       |
| Fire behavior / Brandgedrag / Reaction au feu / Brennverhalten / Fire behavior  | < 100 mm/min          | ISO 3795 1989          |
| EU Directive 2002/72/EC + Amendments (direct food contact materials)  | Conform               |                        |
| Application Packaging and coverage of aqueous foods having a pH > 4.5 (e.g.drinking water) and dry foods (e.g. vegetables, fruits), intended to be used at ambient temperatures   |                       |                        |